

AUG 28 2006

Art Unit 2627
Serial No.: 10/815,494Reply to Office Action of: 07/26/2006
Attorney Docket No.: R1861**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A method for plating CoNiFe in a magnetic recording head comprising a first pole, a second pole, a write coil residing between the first pole and the second pole, and a write gap residing between a portion of the first pole and a portion of the second pole, the method comprising:

(a) providing a plating solution including hydroxymethyl-p-tolylsulfone, the plating solution being configured to provide a CoNiFe film having a high saturation magnetic flux density and having a composition of 50-70 weight percent of Fe and 3-8 weight percent of Ni; and

(b) plating at least a portion of the first pole and/or the second pole using the CoNiFe film on a substrate in the plating solution.

2. (Original) The method of claim 1 wherein the plating solution providing step (a) further includes the step of:

(a1) configuring the plating solution to provide the CoNiFe film having the high saturation magnetic flux density of greater than 2.2 Tesla and having a composition of 58-62 weight percent of Fe and 3.5-4 weight percent of Ni.

Art Unit 2627
Serial No.: 10/815,494

Reply to Office Action of: 07/26/2006
Attorney Docket No.: R1861

3. (Original) The method of claim 1 wherein the plating solution providing step (a) further includes:

(a1) configuring the plating solution to ensure that the CoNiFe film is a soft magnetic film.

4. (Original) The method of claim 3 wherein the CoNiFe film has a hard axis coercivity of less than or equal to two Oe and an easy axis coercivity of less than or equal to six Oe.

5. (Original) The method of claim 1 wherein the plating solution providing step (a) further includes:

(a1) configuring the plating solution to ensure that the CoNiFe film has a low perpendicular anisotropy field of less than thirty five Oe.

6. (Original) The method of claim 5 wherein the CoNiFe film has the low perpendicular anisotropy field of less than twenty Oe.

7. (Original) The method of claim 1 further comprising the steps of:

(c) adjusting the plating solution after step (b) to maintain the plating of the CoNiFe film having the composition and the saturation magnetic flux density; and

(d) plating a second CoNiFe film.

Art Unit 2627
Serial No.: 10/815,494

Reply to Office Action of: 07/26/2006
Attorney Docket No.: R1861

8. (Original) The method of claim 1 wherein the plating solution providing step (a) further includes:

(a1) including CoSO_4 , NiSO_4 , FeSO_4 , NH_4Cl , boric acid, Sodium lauryl sulfate, and saccharin in the plating solution.

9. (Original) The method of claim 1 wherein the plating solution providing step (a) further includes:

(a1) maintaining the plating solution at a pH of less than 3.

10. (Original) The method of claim 9 wherein the plating solution providing step (a1) further includes:

(a1i) maintaining the plating solution at the pH of substantially 2.8.

Art Unit 2627
Serial No.: 10/815,494

Reply to Office Action of: 07/26/2006
Attorney Docket No.: R1861

11. (Original) A magnetic recording head comprising:

a first pole;

a second pole;

a write coil residing between the first pole and the second pole;

a write gap residing between a portion of the first pole and a portion of the second pole;

wherein at least a portion of the first pole and/or the second pole are plated using a plating solution including hydroxymethyl-p-tolylsulfone (HPT), the plating solution being configured to such that the at least the portion includes a CoNiFe film having a high saturation magnetic flux density and having a composition of 50-70 weight percent of Fe and 3-8 weight percent of Ni.

12. (Original) The magnetic recording head of claim 11 wherein the CoNiFe film has the high saturation magnetic flux density of greater than 2.2 Tesla and a composition of 58-62 weight percent of Fe and 3.5-4 weight percent of Ni.

13. (Original) The magnetic recording head of claim 11 wherein the CoNiFe film is a soft magnetic film.

14. (Original) The magnetic recording head of claim 13 wherein the CoNiFe film has a hard axis coercivity of less than or equal to two Oe and an easy axis coercivity of less than or equal to six Oe.

Art Unit 2627
Serial No.: 10/815,494

Reply to Office Action of: 07/26/2006
Attorney Docket No.: R1861

15. (Original) The magnetic recording head of claim 11 wherein the CoNiFe film has a low perpendicular anisotropy field of less than thirty five Oe.

16. (Original) The magnetic recording head of claim 11 wherein the CoNiFe film has the low perpendicular anisotropy field of less than twenty Oe.